

**ABSTRACT OF THE DISCLOSURE**

An anodization-adapted aluminum alloy containing 2.0 to 3.5 wt% Mg and the remainder of 99.9 wt% or greater high-purity aluminum.